

## PRODUCT/PRODUKT INFORMATION

### a l f a – t a b 3 0


**Type: ATAB 0 – 0.3 mm, (– 48 Mesh)**

Chemical Characteristics / Chemische Eigenschaften [%]			
	Typical / Typisch	Min	Max
AL <sub>2</sub> O <sub>3</sub>	99,50	99,30	
Na <sub>2</sub> O	0,30		0,40
SiO <sub>2</sub>	0,04		0,06
Fe <sub>2</sub> O <sub>3</sub> (TOTAL)	0,08		0,13
CaO	0,02		0,06
Fe Magnetic	≤ 0,025		

Physical Characteristics / Physikalische Eigenschaften			
	Typical / Typisch	Min	Max
Bulk Density / Rohdichte	[g/cm <sup>3</sup> ]	3,55	3,50
Apparent Porosity / Offene Porosität	[%]	4,00	5,00
Water Absorption / Wasserabsorption	[%]	1,50	2,00

### Standard Grain Size / Standard Korngröße

Size / Größe	Tyler	Typical / Typisch	Min/Max
[mm]	[mesh]	[%]	[%]
+ 0,30	48	1	0 – 5
+ 0,25	60	5	
- 0,045	325	30	15 – 45



### Standard Packing / Standard Verpackung

- Paper Bags / Papiersäcke 25 kg, 50 kg
- Big bags 1,0 mt, 1,5mt, 2,0 mt
- Bulk / Lose

Rev: 07 - 03